

PRODUCT SOLUTIONS

# DURATEC®

ZEUS® SOLID COLOUR RANGE



**Dulux®**

**POWDER  
COATINGS**




New Zealand

**Worth doing, worth Dulux®**

Worth doing, Worth Dulux.®

The Duratec Zeus solid colour range is a collection on trend solid colours, delivered with warranty grade advanced super durable polyester thermosetting powder.

- ✓ Super durable finish
- ✓ Excellent colour retention
- ✓ On trend solid colours
- ✓ Custom colour service available



Company Name: Crosson Architects.  
The project: DNA House, Otama, New Zealand.  
Company Name: Crosson Architects.  
Photo credit: Simon Devitt.  
2018 Dulux Colour Awards.  
Finalist Single Residential Exterior.

Suitable substrates

- Duratec Zeus are ideal for warranty grade applications over:
- Architectural aluminium including perforated and expanded aluminium.
  - Steel (mild), bright/semi bright steel, black steel and blue steel.

- Duratec Zeus can also be used on the following metals but these are not warranted:
- Galvanised steel, stainless steel and Zinalume®.

Project types

Duratec Zeus is suitable for use on architectural aluminium and steel on most exterior project types greater than 1.0m from the high tide mark. Duratec Zeus is also suitable for most interior projects (including all NZ Building Code Classifications).

	NON-HABITABLE	RESIDENTIAL <4 LEVELS	RESIDENTIAL >3 LEVELS	LIGHT COMMERCIAL <4 LEVELS	COMMERCIAL >3 LEVELS	PRESTIGIOUS COMMERCIAL	MONUMENTAL
INTERIOR	•	•	•	•	•	•	•
EXTERIOR	•	•	•	•	•	•	

- Non-habitable projects are those that are not dwelling types. Examples can be furniture, bus shelters, signage etc.
- Residential properties < 4 levels are typically easy to maintain, given their height and access.
- Light commercial projects <4 levels are sheltered from neighbouring buildings, but require greater durability due to higher usage and wear.
- High-rise residential and commercial projects are less sheltered from neighbouring buildings, raising their exposure and reducing their ease of maintenance.
- Prestigious commercial projects attract attention and require high quality finishes to uphold the longevity and design requirements.
- Monumental projects attract the most attention and have the highest standards required to uphold the reputation and protection expected from landmark sites.

Warranty benefits

The Dulux Duratec Zeus solid colour range are supported by Dulux Alumi Shield™ and Dulux Steel Shield™ warranties when applied by a Dulux Accredited or Dulux Prime Accredited Powder Coater to the warranty specification on recommended project types and conditions.

Alumi Shield™ Warranty	Steel Shield™ Warranty
The Alumi Shield™ warranty is made up of two key components, a colour warranty (for fade and chalking) and a durability warranty (film integrity)	The Steel Shield™ warranty is made up of two key components, a colour warranty (for fade and chalking) and a corrosion warranty
<div>ALUMI SHIELD™ WARRANTY</div> <div>25 YEAR ALUMINIUM DURABILITY WARRANTY</div> <div>20 YEAR ALUMINIUM COLOUR WARRANTY</div>	<div>STEEL SHIELD™ WARRANTY</div> <div>UP TO 10 YEAR STEEL CORROSION WARRANTY</div> <div>20 YEAR STEEL COLOUR WARRANTY</div>

Terms and conditions apply

- The Alumi Shield™ and Steel Shield™ colour warranties are your assurance that Duratec Zeus will not:  
**Fade** – Fade testing will not give a delta E (Hunter) laboratory reading greater than five units from the original colour.  
**Chalk** – The rate of chalking will not exceed a rating of 2 for whites and pastels and a rating of 3 for deep colours as assessed in accordance with AS1580.481.1.11 test method.
- The Alumi Shield™ durability warranty is your assurance the powder coating won't peel, crack or flake during the warranty period, from the date the product is applied to the metal.
- The Steel Shield™ corrosion warranty is your assurance that the coating system will not corrode more 5% in accordance with the degree of corrosion as a percentage contained in AS 2312.1
- Warranties are only valid when applied by a Dulux Accredited or Dulux Prime Accredited Powder Coater to the warranty specification on recommended project types and conditions.

Important design considerations

Dulux Alumi Shield™ and Steel Shield™ warranties are available on a wide range of fabricated architectural aluminium and steel items, but those items must be designed, prepared (pre-treated), coated, fabricated and installed to standard ensuring that the item is fully protected.

It is essential that any item that is coated must be designed and fabricated to ensure:

- **It meets key standards** – Refer to AS 2312.1 and the relevant building code.
- **Protection is a key consideration at the early stages of design** – The design should allow the item to be prepared for coating correctly and that the minimum thickness of the specified coating can be achieved.
- **Sealed areas are appropriately sealed to last the duration of the warranty** – It is essential that the choice of other materials that contribute to protection such as sealants should be made to ensure that a Alumi Shield™ and Steel Shield™ warranty is not void due to the sealants failure. This is important if only one side of a section of metal be coated, it must be in a sealed environment, i.e. not exposed to moisture, air and excessive heat. Should the seal fail, and a claim is made this warranty will be void as the integrity of the seal is not the responsibility of Dulux.
- **The following design elements are avoided** – Narrow crevices, poor air circulation, depressions, sharp edges and corners, large flat ledges (not window ledges), intermittent welding, undrained flat surfaces, unsealed hollow sections, flat surfaces in loose contact where moisture may be drawn in between them by capillary action or where water and foreign matter will lodge, as these areas may result in premature failure of the coating system.
- **Failure caused by post formed or post fabrication processes are avoided** – Please be aware warranties shall not apply to areas where a failure is caused from post formed or post fabrication processes, such as metal perforation, welding or any other circumstances beyond the reasonable control of Dulux. Many post fabrication processes can impede achievement of a continuous layer of pre-treatment and the minimum film build of powder coating. Where there is doubt please consult the relevant guideline or regulation such as the building code or window association for information on mitigating any potential damage that could be caused by post fabrication processes.

For full details on Alumi Shield™ and Steel Shield™ warranties including terms and conditions visit [duluxpowders.co.nz/warranties](http://duluxpowders.co.nz/warranties)

# Project suitability

Use the following tables to help identify where Duratec Zeus can be applied on aluminium and steel projects. Refer to the conditions information to determine the environment that your project will be exposed to.

## Project suitability – aluminium

Project, Environment and Conditions			Top Coat	
Project Type	Environment	Conditions	Duratec Zeus	
			Durability Warranty	Colour Warranty
Monumental	Exterior	Mild, Severe	-	-
Prestigious Commercial	Exterior	Mild, Severe	25 Years	20 Years
Commercial	Exterior	Mild, Severe	25 Years	20 Years
Light Commercial	Exterior	Mild, Severe	25 Years	20 Years
Residential	Exterior	Mild, Severe	25 Years	20 Years
Non Habitable	Exterior	Mild, Severe	25 Years	20 Years
All Projects	Interior	Moderate Interior	25 Years	20 Years
All Projects	Interior	General Interior	25 Years	20 Years

**Duratec Zeus warranties.**

All Duratec Zeus Alumi Shield™ and Steel Shield™ warranties are:

- Only suitable for coastal environments >10m from the high tide
- Not suitable in strongly acidic or caustic environments so the pH must be between 5 and 9.
- Available only when applied by a Dulux Accredited or Dulux Prime Powder Coater to the warranty specification on recommended project types and conditions.

Please refer to page 6 for warranty implications for:

- Interior and exterior environments close to liquids other than the sea
- Geothermal environments.

**Perforated and expanded aluminium**

Alumi Shield™ warranties on perforated and expanded aluminium are available for Duratec Zeus in the following environments:

a. **Interior** – General Interior conditions (E-Prime/Grey Primer base coat not mandatory); Moderate Interior (E-Prime/Grey Primer base coat mandatory).

b. **Exterior** – Mild (E-Prime/Grey Primer base coat not mandatory); Severe: (E-Prime/Grey Primer basecoat mandatory).

For more information about specifications on perforated and expanded aluminium visit [duluxpowders.co.nz/perforated-aluminium](http://duluxpowders.co.nz/perforated-aluminium)

## Project suitability – steel

Corrosion Category			Primer System		Top Coat	
Project Type	Environment	Conditions (including Corrosivity Level)	Zincshield	E-Prime™/ Grey Primer	Duratec Zeus	
					Corrosion Warranty	Colour Warranty
Monumental	Exterior	Mild, Severe	-	-	-	-
Prestigious Commercial	Exterior	Severe (High to very high)	✓	✓	5 Years	20 Years
Prestigious Commercial	Exterior	Mild (Medium)	✓	Optional*	5 or 10 Years*	20 Years
Prestigious Commercial	Exterior	Mild (Low)	✓	-	10 Years	20 Years
Commercial	Exterior	Severe (High to very high)	✓	✓	5 Years	20 Years
Commercial	Exterior	Mild (Medium)	✓	Optional*	5 or 10 Years*	20 Years
Commercial	Exterior	Mild (Low)	✓	-	10 Years	20 Years
Residential	Exterior	Severe (High to very high)	✓	✓	5 Years	20 Years
Residential	Exterior	Mild (Medium)	✓	Optional*	5 or 10 Years*	20 Years
Residential	Exterior	Mild (Low)	✓	-	10 Years	20 Years
Non Habitable	Exterior	Severe (High to very high)	✓	✓	5 Years	20 Years
Non Habitable	Exterior	Mild (Medium)	✓	Optional*	5 or 10 Years*	20 Years
Non Habitable	Exterior	Mild (Low)	✓	-	10 Years	20 Years
All Projects	Interior	Moderate Interior (High)	✓	✓	5 Years	20 Years
All Projects	Interior	Moderate Interior (Medium)	✓	Optional*	5 or 10 Years*	20 Years
All Projects	Interior	General Interior (Very low to low)	✓	-	10 Years	20 Years

**\*Important Primer Advice**

1. In Mild (Medium) exterior environments and Moderate (Medium) interior environments a 10 year corrosion warranty is available with a Zincshield, E-Prime/Grey Primer and a Duratec Zeus top coat system.

2. Without E-Prime/Grey Primer a 5 year corrosion warranty is available.

For all projects in severe conditions it is recommended to speak to a Dulux Account Manager or call the Advice line on **0800 800 975**.

For more information about specifications call our Advice line on 0800 800 975 or visit [duluxpowders.co.nz](http://duluxpowders.co.nz)

## Conditions

Use the following table which references AS 2312.1, SNZ TS 3404 and ISO 9223 to identify the environment, conditions and atmospheric corrosivity categories. To further pinpoint your project this table can be used together with the Dulux Macrocclimate Corrosivity Zone Maps of New Zealand Guide available at [duluxpowders.co.nz](http://duluxpowders.co.nz)

Environment	Conditions	Corrosivity Zone <sup>4</sup>	Aluminium Corrosion Rate (g/m2) <sup>5</sup>	Carbon (Mild) Steel Corrosion Rate (g/m2) <sup>4</sup>	Example Environments
Exterior Environment	Mild	C2 Low	≤ 0.6	10–200	Arid, dry, urban, inland, city
		C3 Medium	0.6 – ≤ 2.0	200–400	Light Industrial, geothermal (>500m from source) <sup>1</sup> and inland coastal (mild sea spray zone)
	Severe	C4 High	2 – ≤5	400–650	Sea shore (medium sea spray zone), offshore Islands <sup>3</sup> and or geothermal (<500m from source) <sup>2</sup>
		C5 Very High Marine & Industrial	5 – ≤10	650–1500	Sea shore (high sea spray zone e.g. surf), offshore Islands <sup>3</sup> and heavy industrial

Environment	Conditions	Corrosivity Zone <sup>4</sup>	Aluminium Corrosion Rate (g/m2) <sup>5</sup>	Carbon (Mild) Steel Corrosion Rate (g/m2) <sup>4</sup>	Example Environments
Interior Environments	General Interior	C1 Very Low	Negligible	<10	Dry interiors (homes, offices, shops)
		C2 Low	≤ 0.6	10–200	Minor condensation (warehouses, sports halls)
	Moderate Interior	C3 Medium	0.6 – ≤ 2.0	200–400	High moisture (dairy and food processing plants, breweries, and commercial laundries)
		C4 High	2 – ≤5	400–650	Significant contamination (swimming pools)

1. Geothermal environments greater than 500m of a bore, mud pool, steam vent, or other source with a pH between 5 and 9. For a pH outside this consult Dulux.

2. Geothermal hot spots within 500m of a bore, mud pool, steam vent, or other source.

3. All offshore islands including Waiheke Island, Stewart Island, Fraser Island and Pacific islands e.g. PNG, Fiji, Samoa, Tonga, Tahiti, Noumea.

4. The corrosion rates for the first year of exposure for the different corrosivity categories of Aluminium and Carbon (Mild) Steel are determined by the following standards:

  - SNZ TS 3404 - Standards NZ Technical Specification – Durability requirements for steel structures & components.
- AS 2312.1 - Guide to the protection of structural steel against atmospheric corrosion by the use of protective coatings. Part 1: Paint coatings
  - ISO 9223 - Corrosion of metals and alloys – Corrosivity of atmospheres – Classification, determination and estimation

5. The corrosion rates for the first year of exposure for the different corrosivity categories of aluminium are determined by the following standard:

  - ISO 9223 - Corrosion of metals and alloys – Corrosivity of atmospheres – Classification, determination and estimation.

Important warranty considerations

Your warranty can also be impacted by its proximity to liquids other than the sea and geothermal environments whilst a regular care and maintenance program must be implemented for warranty compliance.

Interior and exterior environments close to liquids other than the sea

For powder coated assets close to liquids other than the sea, e.g. fences near swimming pools, fountains, bathrooms or furniture etc, please refer to the guidance below to understand the warranty limitations in these environments.

	ChemicallyTreated <sup>1</sup>	Clean tap, Fresh or Potable Water	Salt Water <sup>1</sup>	Other
Duratec Zeus	◆	●	◆	Seek advice from Dulux Call 0800 800 975

1. Aggressive liquids such as Chemically Treated liquids and Salt Water must be cleaned off immediately as per the Dulux Care and Maintenance guide. Please note chemically treated water includes antimicrobial treatments, e.g. in pools, anti-corrosive chemicals, and soapy water in bathrooms and showers.

- ◆ Where indicated Alumi Shield™ and Steel Shield™ warranties are available on areas >than 1m from the liquid.
- Where indicated Alumi Shield™ warranties are available any distance from the liquid.

Alumi Shield™ and Steel Shield™ warranties are only available when applied by a Dulux Accredited Powder Coater to the warranty specification on recommended project types and conditions.

All Dulux powder product are NOT suitable in strongly acidic or caustic environments so the pH must be between 5 and 9.

Alumi Shield™ and Steel Shield™ warranties are not available if the powder coating is immersed in any liquid.

Geothermal environments

For powder coated assets close to geothermal zones, the choice of product is dependent on the level of geothermal activity and specifically the distance from the geothermal source. As Duratec Zeus is super durable it is suitable for environments close to geothermal activity (within 500m of the source) and beyond. The corrosion zones or categories still apply based on distance from the sea and other factors.

* Distance to Geothermal Environment	Duratec Zeus
Less than 500m from source	✓
Greater than 500m from source	✓

\* Distance from bore, mud pool, steam vent, or other source with a pH between 5 and 9. For a pH outside this consult Dulux.

For more information about specifications in geothermal environments visit [duluxpowders.co.nz/geothermal](https://duluxpowders.co.nz/geothermal)

Care and maintenance

Care and maintenance is essential for warranty compliance

To ensure the life of your asset is maximised and to comply with Dulux Alumi Shield™ and Steel Shield™ warranty requirements, a simple and regular maintenance program must be implemented and recorded in line with the Dulux Care and Maintenance of Powder Coated Surfaces brochure.



For more information refer to the Dulux Care and Maintenance of Powder Coated Surfaces brochure visit [duluxpowders.co.nz/tech-advice](https://duluxpowders.co.nz/tech-advice)

Product summary

Product Features	
Warranties	Alumi Shield™ and Steel Shield™ available – refer to Warranty Benefits.
Technology	Super durable polyester thermosetting powder.  It is recommended that each project is coated with the same batch of powder, by the same applicator, in the same direction, i.e., all vertically or all horizontally and if possible at the same time. This is especially important when large visible areas of a project are powder coated, for example, cladding and perforated and expanded aluminium sheets.
Look	Solid colour
Finish	Matt, satin and gloss
Colour range	Available in a comprehensive range of core colours.  View the range in Dulux Colour Selectors, on aluminium swatches, or online. Cards and swatches can be ordered from <a href="https://duluxpowders.co.nz">duluxpowders.co.nz</a> . If you cannot find the colour you require Dulux can offer a Custom Colour Service. Call 0800 900 975 or visit <a href="https://duluxpowders.co.nz">duluxpowders.co.nz</a>
Standards met	Formulated to meet: AS 3715, AAMA 2603 and AAMA 2604.  <b>Reaction to fire test results:</b>  Classification of fire performance for Duratec has a Group Number Classification of 1 according to the National Construction Code (NCC) Volume One Specifications C1.10 of the Building Code of Australia (BCA) and a Group Number Classification of 1-S according to the NZ Building Code Verification Method C/VM2 Appendix A: Establishing Group Numbers for lining materials.  Also available is testing results for Industry Standard: AS/NZS1530.3.  For more information call 0800 900 975 or refer to the Duratec: Reaction to fire test results brochure available at <a href="https://duluxpowders.co.nz">duluxpowders.co.nz</a>
Product Benefits	
Colour retention	Excellent colour retention.
Durability	Super durable finish.
Aesthetic	Long lasting, on trend solid colours.

Meets international standards

With over 50 years of experience, the AAMA (American Architectural Manufacturer’s Association) is regarded as the standards leader for finishes on architectural aluminium. Dulux Duratec Zeus is formulated to meet: AAMA 2603 and AAMA 2604 as well as Australian standard AS 3715.

For more information visit [aamanet.org](https://aamanet.org)

Securing your warranty

Dulux Accredited Powder Coaters

Only Dulux Accredited and Dulux Prime Accredited Powder Coaters are able to issue our Dulux Alumi Shield™ and Steel Shield™ warranties after demonstrating their capability to meet stringent quality conditions and international standards. Warranties are only valid when applied by a Dulux Accredited or Dulux Prime Accredited Powder Coater to the warranty specification on recommended projects, and subject to specified warranty terms and conditions.



For more information visit [duluxpowders.co.nz/accredited](https://duluxpowders.co.nz/accredited)



## Advice line

Our dedicated consultants can help simplify the specification process, saving you time and money by providing the right coating advice for your project. They can provide:

- Documented project specific specifications
- Written confirmation of your project's eligibility for an Alumi Shield™ or Steel Shield™ warranty
- Design, coating system and colour advice

Call 0800 800 975 or visit **[duluxpowders.co.nz](http://duluxpowders.co.nz)**

## Offices

### New Zealand

Dulux Powder Coatings  
31B Hillside Road  
Glenfield, Auckland 0627  
T (64) 4 896 0911

### Australia

Dulux Powder Coatings  
1-15 Pound Road West  
Dandenong South VIC 3175  
T (61) 3 8787 4500

### Singapore

DGL International Powder Coatings  
100 Pasir Panjang Road  
#02-10, Singapore 118518  
T (65) 6 8381 010

### China

DGL International Powder Coatings  
Room 406, No.8, Lane 1977, JinShaJiang Road  
Shanghai, China, PC 200333  
T (86) 21 6173 8800



**Dulux®**

**POWDER  
COATINGS**

Dulux, Duralloy, Duratec, Electro device mark, Fluoraset, Zincshield, Worth doing, worth Dulux and Dulux World of Colour are registered trade marks and Alumi Shield, Steel Shield, EPrime and Dulux Accredited Powder Coater are trade marks of DuluxGroup (Australia) Pty Ltd. Copyright 2020 DuluxGroup (Australia) Pty Ltd. Zinalume is a registered trade mark of Bluescope Steel Limited.

**Worth doing, worth Dulux.®**